



# TECHNICAL DATA SHEET

BACKSTOP® NTX™

A High Performance, Polymer-Based,  
Noncementitious Water-Resistive  
Membrane and Air Barrier  
DS806

---

## PRODUCT DESCRIPTION

### FOR USE BENEATH CLADDINGS OTHER THAN DRYVIT® EIFS

Backstop® NTX is a flexible, polymer- based, non-cementitious, air/water-resistive barrier membrane, which resists water penetration, eliminates air infiltration, and is vapor permeable. Backstop NTX is designed for vertical exterior, above-grade walls.

Backstop NTX is available in three versions:

- **Backstop NTX - Texture** is applied using a trowel, roller, or texture spray equipment.
- **Backstop NTX - Smooth** is applied by roller or airless spray equipment.



---

## BASIC USES

Backstop NTX – Texture and Smooth are designed for use with exterior building cladding systems. When used with the Dryvit AquaFlash® System, Dryvit Backstop Flash and Fill, or Dymonic® 100, Backstop NTX provides an effective air barrier and water-resistive membrane for acceptable substrates.

---

## FEATURES & BENEFITS

### FEATURES

- Includes options for reinforcing fabric at sheathing joints
- Bonds to most construction materials
- Fluid applied/Fast drying
- Can be exposed for 180 days
- Cold Weather Application 25 °F (-4 °C)

### BENEFITS

- Ensures a continuous film barrier across transitions
- No need for multiple products
- Easy to use
- Not subject to tear off or damage from wind

---

## PROPERTIES

**Working Time:** Backstop NTX – Texture and Smooth are noncementitious, water based materials and will not set-up in the pail. Keep pail covered when not in use to minimize skinning.

**Drying Time:** The drying time is dependent upon the air temperature, wind conditions and relative humidity. Under average drying conditions [70 °F (21 °C), 55% R.H.], Backstop NTX will be dry to the touch within 2 hours and cure in 6 hours.

**Testing Information:** For test data refer to the chart included with this document.

**Application Procedure:** For complete application instructions refer to [DS300](#).

**Job Conditions:** Air and surface temperature for application of Backstop NTX must be from 25 °F (-4 °C) minimum to 100 °F (38 °C) maximum and must remain so for a minimum of 12 hours.

**Temporary Protection:** Shall be provided at all times until membrane is dry and shall not be exposed to weather for longer than 180 days prior to installation of the specified cladding.

## Acceptable Substrates:

All sheathing substrate joints must be treated prior to the application of the Backstop WRB. Options include: Dryvit Grid Tape and Backstop NTX – Texture; Dymonic 100; Backstop NTX Smooth and Aquaflash mesh.

Acceptable substrates include:

- Core treated exterior grade gypsum sheathing meeting ASTM C 1396 (formerly C 79).
- Core treated exterior grade gypsum sheathing with fiberglass mat facers meeting ASTM C 1177.
- Exterior fiber reinforced cement or calcium silicate boards.
- APA Exterior or Exposure 1 Rated Plywood, Grade C-D or better, nominal 1/2 in (12.7 mm) minimum, 4-ply.
- APA Exterior Grade Fire Retardant Treated Plywood, nominal 1/2 in (12.7 mm) minimum.
- APA Exposure 1 Rated OSB, nominal 1/2 in (12.7 mm) minimum. (See limitations).
- Unpainted, unsealed concrete and CMU.

## BACKSTOP NTX (BSNTX) – TEXTURED AND SMOOTH USAGE/APPLICATION CHART

			APPROX. COVERAGE PER PAIL	APPROX. COVERAGE/DRUM
<b>EXTERIOR GRADE GYPSUM SHEATHING</b>				
	BSNTX - Texture	Trowel	300 lin. Ft (91 m)	
	BSNTX - Smooth	1/2 in (12.7 mm) Nap Roller or Airless Sprayer	500 ft <sup>2</sup> (45 m <sup>2</sup> )	
Joints <sup>a</sup>	Dymonic 100	Putty knife	20 oz (.59 L) SSG covers 6.3 ft <sup>2</sup> (9.75m) AT 40 mils X 1.50" (1 mm X 38 mm) joint	
	Backstop flash and fill	Putty knife	20 oz (.59 l) SSG covers 15-17 ft <sup>2</sup> (1.39 – 1.58 m <sup>2</sup> ) at 12-15 wet mils (0.30 – 0.38 mm)	
Face <sup>e</sup>	BSNTX - Texture	Trowel, FoamPRO #58 Roller <sup>b</sup> or Texture Sprayer	250-300 ft <sup>2</sup> (23-27 m <sup>2</sup> )	
	BSNTX – Smooth <sup>c-g</sup>	1/2 in (12.7 mm) Nap Roller	500 ft <sup>2</sup> (46 m <sup>2</sup> )	
	BSNTX – Smooth <sup>c-g</sup>	Airless Sprayer	500 - 600 ft <sup>2</sup> (46-55 m <sup>2</sup> )	5000-6000 ft <sup>2</sup> (465-557m <sup>2</sup> )
<b>FIBERGLASS FACED EXTERIOR GYPSUM SHEATHING</b>				
Joints <sup>a</sup>	BSNTX - Texture	Trowel	300 lin. ft (91 m)	
	BSNTX - Smooth	1/2 in (12.7 mm) Nap Roller or Airless Sprayer	400-500 ft <sup>2</sup> (37-46 m <sup>2</sup> )	
Face <sup>e</sup>	BSNTX - Texture	Trowel or Texture Sprayer	250-300 ft <sup>2</sup> (23-27 m <sup>2</sup> ) [includes joints]	
	BSNTX - Smooth <sup>c-g</sup>	1/2 in (19 mm) Nap Roller	400 ft <sup>2</sup> (37 m <sup>2</sup> )	
	BSNTX - Smooth <sup>g</sup>	Airless Spray	500-600 ft <sup>2</sup> (46-56 m <sup>2</sup> )	5000-6000 ft <sup>2</sup> (465-557m <sup>2</sup> )
<b>EXPOSURE 1, EXTERIOR GRADE, AND FIRE RETARDANT TREATED PLYWOOD; AND EXTERIOR CEMENT BOARD</b>				
Joints <sup>a</sup>	BSNTX - Texture	Trowel	300 lin. Ft (91 m)	
	BSNTX - Smooth	1/2 in (12.7 mm) Nap Roller or Airless Sprayer	400-500 ft <sup>2</sup> (37-46 m <sup>2</sup> )	
Face <sup>e</sup>	BSNTX - Texture	Trowel, FoamPRO #58 Roller <sup>b</sup> or Texture Sprayer	250-300 ft <sup>2</sup> (23-27 m <sup>2</sup> )	
	BSNTX - Smooth <sup>c-g</sup>	1/2 in (12.7 mm) Nap Roller	400 ft <sup>2</sup> (37 m <sup>2</sup> )	
	BSNTX - Smooth <sup>g</sup>	Airless Spray	500-600 ft <sup>2</sup> (46-56 m <sup>2</sup> )	5000-6000 ft <sup>2</sup> (465-557 m <sup>2</sup> )
<b>APA EXPOSURE 1 RATED ORIENTED STRAND BOARD (OSB)</b>				
Joints <sup>a</sup>	BSNTX - Texture	Trowel	300 lin. ft (91 m)	
	BSNTX - Smooth	1/2 in (12.7 mm) Nap Roller or Airless Sprayer	300-400 ft <sup>2</sup> (27-37 m <sup>2</sup> )	
Face <sup>e</sup>	BSNTX - Smooth <sup>c-g</sup>	1/2 in (12.7 mm) Nap Roller	350-400 ft <sup>2</sup> (32-37 m <sup>2</sup> )	
	BSNTX - Smooth <sup>g</sup>	Airless Spray	300-400 ft <sup>2</sup> (27-37 m <sup>2</sup> )	3000-4000 ft <sup>2</sup> (325-372 m <sup>2</sup> )
<b>CONCRETE AND MASONRY<sup>d,g</sup></b>				
Face	BSNTX - Texture	Trowel <sup>f</sup>	250-300 ft <sup>2</sup> (23-27 m <sup>2</sup> ) applied in 1 coat	
	BSNTX - Texture	FoamPRO #58 Roller or Texture Sprayer	200-250 ft <sup>2</sup> (18-23 m <sup>2</sup> ) applied in 2 coats,	
	BSNTX - Smooth <sup>g</sup>	Airless Spray	350-500 ft <sup>2</sup> (32-46 m <sup>2</sup> ) applied in 2 coats, backrolled	3500-5000 ft <sup>2</sup> (325-464 m <sup>2</sup> )

<sup>a</sup> Tape the joints with Dryvit Grid Tape prior to application of Backstop NTX - Texture at joints and screw heads.

<sup>b</sup> Up to 1 pint (16 oz) of water may be added to a 60 lb pail of Backstop NTX - Texture for roller or spray applications only. The FoamPRO #58 roller cover (FoamPRO Mfg., Inc., [www.foampromfg.com](http://www.foampromfg.com)) is available at home supply stores.

<sup>c</sup> Because of application methodology and absorptive surface differences, two coats may be required to obtain this coverage.

<sup>d</sup> Due to variations in types of concrete/masonry, apply a 6 ft x 6 ft test area with coverage as indicated in the chart, before proceeding with the entire job. If there are voids in the substrate, particularly at the mortar joints, the job should be parged with Genesis<sup>®</sup>, 24 hours prior to BSNTX - Texture application. Backstop NTX shall NOT be used as a skim coat for parging CMU joints or heavy textured units.

- e Backstop NTX - Texture (with up to 1 pint water addition per 60 lb. pail) or Smooth may be sprayed and backtrowelled/backrolled.
  - f Coverage may vary depending on the texture and porosity of the substrate. Coverage assumes a smooth, dense surface.
  - g Backstop NTX should be applied at the recommended coverage rates to form a continuous film free of voids, pinholes or other discontinuities. The following approximate mil thicknesses are recommended:

Backstop NTX Texture	13 DFT	20* WFT
Backstop NTX Smooth	9 DFT	14* WFT
  - \* Based on volume solids
- Refer to Product Data Sheets for Complete Mixing and Application Instructions

---

## SURFACE PREPARATION

- Sheathing board gaps shall not exceed 1/4 in (6.4 mm) and the surface must be flat within 1/4 in (6.4 mm) in any 4 ft (1.2 m) radius. CMU mortar joints shall be struck flush (tooled mortar joints and heavily textured CMU [not split faced] shall be skimmed with Dryvit Genesis®, Genesis® DM or Genesis® DMS) prior to application of the Backstop NTX – Texture. CMU shall be clean, unpainted and free of efflorescence. All substrates shall be dry and free of foreign materials such as dirt, dust, oil, paint, wax, water repellants or other materials that inhibit adhesion.
- Concrete: Shall have cured a minimum of 28 days prior to application of the finishes. If efflorescence, form release agents or curing compounds are present on the concrete surface, the surface shall be thoroughly washed with muriatic acid and flushed to remove residual acid. All projections shall be removed and small voids filled with Dryvit Primus®, Primus®DM, Genesis®, or Genesis®DM mixture (see product data sheets for mixing and application).
- All substrate transitions and gaps between openings and penetration components such as windows, doors, electrical boxes, etc., shall be treated with Backstop NTX - Texture, Dryvit AquaFlash®. Any sealants used shall be tested for compatibility and comply with ASTM C 920.
- All opening terminations, roof/wall intersections, transitions between different materials, chimneys, decks, roof, windows, etc., must be properly flashed, wrapped and sealed as required by the building code, good construction practice and/or Dryvit Backstop NTX Application Instructions For Use Beneath Claddings Other Than Dryvit EIFS, [DS300](#).

---

## MIXING

Material is ready for use after an initial spin-up using a drill with paddle mixer. **DO NOT ADD CEMENT.**

---

## APPLICATION

**Backstop NT Application:** Refer to the usage/application chart for the appropriate use and application technique for a given substrate.

---

## COVERAGE

Backstop NTX – Texture and Smooth are supplied in a 5 gal (19 L) pail.

Coverage will vary, depending on application method and substrate. For guidance refer to the usage chart included in this document.

---

## STORAGE

Backstop NTX must be stored at a minimum of 40 °F (4 °C) and a maximum of 100 °F (38 °C) in tightly sealed containers protected from weather and out of direct sunlight.

The shelf life is 2 years from date of manufacture when properly stored in unopened pails.

---

## CLEAN UP

Clean tools with water while material is still wet.

---

## TECHNICAL AND FIELD SERVICES

Available on request.

---

## CAUTIONS & LIMITATIONS

- Apply to acceptable substrates only.
- OSB - Backstop NTX - Texture is not recommended for use in the field of OSB.
- CMU - Application over unpainted concrete and CMU requires one of the following:
  - a. Two coats of Backstop NTX- Smooth, spray or roller-applied.
  - b. One coat of Backstop NTX – Texture, trowel applied.
- Shall not be used below grade or on surfaces that will be subjected to water immersion.

- Shall not be used to treat holes or sheathing joints exceeding 1/4 in (6.4 mm).
- When used beneath Portland cement stucco or adhered stone products, paper backed lath shall be installed over Backstop NTX as a slip sheet.
- Backstop NTX can be exposed to weather up to 180 days to provide sufficient time for installation of the cladding. Inspect the surface of the Backstop NTX for any damage, cracks, voids or other detrimental conditions and repair prior to installation of the cladding.

BACKSTOP® NTX™ - TEXTURE, SMOOTH AND SPRAY TESTING			
TEST	TEST METHOD	CRITERIA	RESULTS
Surface Burning Characteristics	ASTM E 84	ICC and ANSI/EIMA 99-A-2001 Flame Spread <25 Smoke Developed <450	Passed
Flexibility	ASTM E 96 Procedure B ICC ES (AC212)*	No ICC or ANSI/EIMA Criteria	No cracking at 2 mm diameter
Water Vapor Transmission	ASTM E 96 Procedure B ICC ES (AC212)*	ICC: Vapor Permeable No ANSI/EIMA Criteria	17 Perms
Freeze-Thaw Resistance	ASTM E 2485/ICC-ES Procedure (AC212)*	ICC: 10 cycles No deleterious effects <sup>1</sup>	Passed - 10 cycles: No deleterious effects <sup>1</sup>
Water Resistance	ASTM D 2247 ICC ES (AC212)*	ICC: 14 days exposure No deleterious effects <sup>1</sup>	No deleterious effects <sup>1</sup> after 14 days exposure
Tensile Strength and Elongation	ASTM D 2370	No ICC or ANSI/EIMA Criteria	Tensile strength:240 psi Elongation: 250%
Wind Driven Rain	Fed TT-C-555	No ICC or ANSI/EIMA Criteria	No water penetration
Nail Sealability	ASTM D1970	No ICC or ANSI/EIMA Criteria	Passed ABAA Criteria
Air Leakage	ASTM E 283	No ICC or ANSI/EIMA Criteria	0.0014 cfm/ft <sup>2</sup> (0.0071 l/sec/m <sup>2</sup> )
Air Permeance	ASTM E 2178	No ICC or ANSI/EIMA Criteria	0.0005 cfm/ft <sup>2</sup> @ 1.6psf (0.002 l/s/m <sup>2</sup> @ 75Pa)
Air Barrier Assembly	ASTM E 2357	No ICC or ANSI/EIMA Criteria	<0.0016 cfm/ft <sup>2</sup> @ 1.6 psf (0.0079 l/sec m <sup>2</sup> @ 75 Pa)
Structural Performance	ASTM E 1233 Procedure A ICC ES (AC212)*	ICC: Minimum 10 positive cycles at 1/240 deflection; No cracking in field, at joints or interface with flashing.	Passed
Racking	ASTM E 72 ICC ES (AC212)*	ICC: No cracking in field, at joints or interface with flashing at net deflection of 1/8 in (3.2 mm)	Passed
Restrained Environmental	ICC-ES Procedure ICC ES (AC212)*	ICC: 5 cycles; No cracking in field; at joints or interface with flashing	Passed
Water Penetration	ASTM E 331 ICC ES (AC212)*	ICC: No water penetration beyond the inner-most plane of the wall after 15 minutes at 2.86 psf (137 kPa)	Passed
Tensile Bond	ASTM C 297/E 2134 (formerly EIMA 101.03) ICC ES (AC212)*	ICC and ANSI/EIMA 99-A-2001 Minimum 15 psi (104 kPa)	Substrates: Minimum 26 psi (179.3 kPa)
Weathering			
UV Exposure	ICC ES Proc. / ICC ES (AC212)*	ICC: 210 hours of exposure	Passed
Accelerated Aging	ICC ES Proc./ICC ES (AC212)*	ICC: 25 cycles of wetting and drying	Passed
Hydrostatic Pressure Test	AATCC 127 ICC ES (AC212)*	ICC: 21.6 in (549 mm) water column for 5 hours	Passed

\* AC212 – Acceptance Criteria for Water-Resistive Coatings Used as Water-Resistive Barriers over Exterior Sheathing, also referred to as ASTM E 2570

<sup>1</sup> No cracking, checking, rusting, crazing, erosion, blistering, peeling, or delamination when viewed under 5x magnification.

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit products as of the date of publication of this document and is presented in good faith. Dryvit assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit.

For more information on Dryvit or Continuous Insulation, [click here](#).

Printed in USA. Issued 8.17.2022  
©Dryvit 2022

DS806

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



[dryvit.com](http://dryvit.com) | 800.556.7752



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)