



NOTE:
 1. APPLY DYMONIC 100 AT 40 MILS 1" (25 MM) MIN. ONTO FACE OF SECUROCK EXOAIR 430 PANEL AND 1 1/8" (41 MM) MIN. INTO ROUGH OPENING OR PAST PRIMARY SEAL OF WINDOW.

The architecture, engineering, and design of the project using the Dryvit, Tremco and USG products are the responsibility of the project's design professional. All products and systems must comply with local building codes and standards. This detail is for general information and guidance only and Dryvit, Tremco and USG specifically disclaims any liability for the use of this detail. The project design professional determines, in its sole discretion, whether this detail or a functionally equivalent detail is best suited for the project. This detail is subject to change without notice. Contact Dryvit, Tremco and USG to ensure you have the most recent version.



Dryvit Technical Support: 800-556-7752

StucCoat One Coat® Securock® ExoAir 430 System

 SECUROCK® EXOAIR® 430 <small>Technical Support: 866-209-2404</small>	Detail: Rough Opening Preparation - Tremco Dymonic 100 Option			File Name:		 TREMCO <small>Construction Products Group</small>
	Drawn by: KAB	Checked by: BD/CB	Scale: NTS	Date: 4/2023	SCOC SE430 3	
www.tremcocpg.com						